

Technical Datasheet



Application: Plastic and rubber vapour control layers EN 13984

Style name **8207A** Language **English**
Type of carrier **DuPont™ Typar® (PP) with a compound of PP & PE**

PROPERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
Product designation acc. to EN 13984	-	-	A	-	-
FUNCTIONALITY: WATER VAPOR AND AIR TIGHTNESS					
Water vapour transmission (sd)	EN 1931	m	23	18	33
Density of water vapour flow rate (g)	EN 1931	kg / (m ² s)	1,8E-8	1,2E-8	2,3E-8
Temperature resistance	-	°C	-	-40	+80
Durability (exposure to artificial ageing)					
Water vapour transmission properties	EN 1931	pass / no pass	pass	-	-
Bendtsen airpermeability	ISO 5636/3	ml/min	0	-	10
Gurley airpermeability	ISO 5636/5	s	-	>2000	-
PHYSICAL AND MECHANICAL PROPERTIES					
Mass per unit area	EN 1849-2	g/m ²	102	92	112
Thickness	EN 1849-2	mm	0,30	0,23	0,37
Water tightness	EN 1928 (A)	pass / no pass	pass	-	-
Reaction to fire	EN ISO 11925-2	class	E	-	-
Maximum tensile force (MD)	EN 12311-2	N/50mm	200	160	-
Elongation at max. tensile force (MD)	EN 12311-2	%	38	25	-
Maximum tensile force (XD)	EN 12311-2	N/50mm	170	110	-
Elongation at max. tensile force (XD)	EN 12311-2	%	38	23	-
Resistance to tearing MD (nail shank)	EN 12310-1	N	240	180	-
Resistance to tearing XD (nail shank)	EN 12310-1	N	240	180	-
ADDITIONAL PROPERTIES					
Length (customer related, expressed in m)	EN 1848-2	deviation in %	0	0	-
Width (customer related, expressed in mm)	EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness	EN 1848-2	mm	-	-	75
Resistance to impact	EN 12691	mm	(+)	-	-
Joint strength	EN 12317-2	N/5cm	-	150	-
Durability (against alkali)					
Elongation at max. tensile force (MD)	EN 12311-1	pass / no pass	(+)	-	-
Elongation at max. tensile force (XD)	EN 12311-1	pass / no pass	(+)	-	-

(+): No Performance Determined

Effective date : 15/03/2011

First CE: 03/08/2010

DuPont de Nemours (Luxembourg) S.à r.l.
Rue General Patton, L-2984 Luxembourg

Tel +352 3666 5885
Fax +352 3666 5021
tyvek.info@lux.dupont.com
www.construction.tyvek.com

Some test methods are modified according to the EN13984 and/or according to the DuPont ISO 9001:2008 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of the Member States relating to construction products ("European Construction Products Directive"). It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.



Tyvek.

Part of the DuPont™ Tyvek® family